PAVE

TECHNICAL SPECIFICATION

Manufacturing method : Design tufted Pile type : Loop pile

Pile fibre : 100% polyamide 6

solution-dyed Econyl

: 20

Gauge : 1/10"
Pile weight : 620 gr/m²

Pile height : 3.0 - 6.0 mm

Total weight : 4200 gr/m²

Total thickness : 5.8 - 8.8 mm

Tuft density : 177.750 m²

Tile size : 50 x 50 cm

Backing : Polyflex

PERFORMANCE

Tiles per box

Use classification : 23 + 33Caster chair test : 23 + 33: A, intensive use

Abrasion EN 1963 : Pass Vettermann test EN 1471 : Pass Dimensional stability EN 986 : Pass

Thermal isolation ISO 8302 : 0.079 m² K/W

Sound absorption ISO 140-8 : 26 dB
Luxery class : LC2
DOP-nr : 1016-2612
Prodis-nr : in application

ELECTROSTATIC

FLAMMABILITY

Reaction to fire EN ISO 9239-1 : Bfl-s1


Reaction to fire BS 4790 : Low radius of

effect of ignition

COLOUR FASTNESS

Light ISO 105 B02 : 7.0 - 8.0 Rubbing ISO 105 x12 : 4.0 - 5.0 Water ISO 105 E01 : 4.0 - 5.0





INSTALLATION

Before installation, check that tiles are from the same dye batch number. Batches should not be mixed in the same location. All floor surfaces should be clean, dry and flat. Tiles should be left at room temperature for at least 24 hours before fitting.

LAYING DIRECTIONS

Before installation, check that tiles are from the same dye batch number. Batches should not be mixed in the same location. All floor surfaces should be clean, dry and flat. Tiles should be left at room temperature for at least 24 hours before fitting.





CUTTING

Cut with a Stanley knife or similar, preferably from the back, then part the surface pile.

MAINTENANCE

Regular vacuum cleaning is essential. Spills and surface stains can be removed by sponging with a damp cloth, or for more resistant stains, with a mild detergent solution.



















It is strongly recommended that a protecting mat i.e. keyhole mat or similar is used under castor chairs. Colours may vary from those shown on the sampling due to the manufacturing process. No claims will be considered as a result of improper application, installation of maintenance. Pile pressure marks shading and soiling are not manufacturing defects. all specifications are approx.

All Rights reserved to alter technical specifications

Betap Tufting BV
P.O. Box 119, 8280 AC Genemuiden
The Netherlands
T +31(0)38 386 10 60
E centralmail@betap.com
I www.betap.com

