

TASMAN



180




103



129




139



114



124



169



121



131



179



BEST IN PURE WOOL **SINCE 1982**

2016-11

TASMAN



WIDTH 400-500
BREITE
LARGEUR

THERMAL CONDUCTIVITY $m^2 / K/W$ 0.19
WÄRMEDURCHLASSWIDERSTAND $m^2 / K/W$
RESISTANCE THERMIQUE $m^2 / K/W$

PILE FIBRE COMPOSITION 100% Pure New Zealand Wool
MATERIAL DER NUTZSCHICHT 100% reine Neuseeland Schurwolle
COMPOSITION DU VELOURS 100% Pure laine vierge de Nouvelle Zélande

LUXURY CLASS LC 5
LUXUSKLASSE
CLASSE DE LUX

YARN SPECIFICATION 2-ply yarn, stock dyed
GARNE-SPEZIFIKATION 2-fach Garn, flockegefärbt
SPÉCIFICATIONS DU FIL Fil 2 bouts, teint en bourre

FLOORSYMBOLS
TEPPICHBODENSYMBOLLEN
SYMBOLES DE SOL


MASS OF PILE g/m^2 1.695
POLEINSATZGEWICHT g/m^2
MASSE TOTALE g/m^2



TOTAL MASS g/m^2 2.672
GESAMTGEWICHT g/m^2
MASSE TOTALE g/m^2



NUMBER OF TUFTS / m^2 230.000
NOPPENZAHL / m^2
NOMBRE DE TOUFFES / m^2



TOTAL THICKNESS in mm 11.5
GESAMTDICKE in mm
ÉPAISSEUR TOTALE in mm

JAMES
THE FINISHING TOUCH



BEST IN PURE WOOL

SINCE 1982